



# DURASCRIM

POLYESTER REINFORCING FABRIC FOR USE WITH DURAM MEMBRANES AND COATINGS

## Description

Open weave polyester reinforcing fabric for the use of reinforcing Duram waterproofing membranes.

Available in the following roll sizes:

- » 100mm x 10m
- » 150mm x 10m
- » 300mm x 10m
- » 100mm x 50m
- » 150mm x 50m
- » 1.2m x 50m
- » 140mm x 200m A70

## Uses

As a reinforcing fabric, Duram Durascrim is suitable to use with the following Duram Membranes:

Durabit EF, Durabit Reo, Durabit-Bitumen Free, Azcoflex, Pondseal, Duram 195 and Multithane, Azcothane.

Reinforcing membranes with Durascrim is recommended over joins, cracks, gaps and in corners or wherever additional tensile strength or membrane build up is desired.

## Suitable Surfaces

Refer to product data sheet for the particular Duram waterproofing product.

## Specification

The information contained in this product data sheet is typical but does not constitute a full specification as conditions and specific requirements may vary from project to project. The instructions should be considered as a minimum requirement but the applicator or contractor must use their skill, knowledge and experience to carry out additional works as may be necessary to meet the requirements of the project. Specification for specific projects should be sought from the Company in writing.

## Benefits and Advantages

By using Durascrim:

- Provides additional strength to waterproofing membranes.
- Allows greater product build up.

## Application

Apply 1st coat of the Duram membrane, usually at no less than 500 microns thick, and embed the Durascrim into wet coat. Apply a similar saturating coat over and working it in to the Durascrim ensuring that there are no wrinkles, folds or bubbles in fabric and sufficient product has been applied to cover the fabric. Allow to dry. Apply 1 to 2 additional coats at 500 microns thick and allow to dry.

Refer to product data sheets of the Duram membrane in question.

## Coverage

The stated average coverage rate may vary depending upon type, condition, porosity, texture of the surface and application technique.

Generally, at least 2 litres per m<sup>2</sup> of product is needed to properly saturate and cover Durascrim.

## Colours

White.

## Storage

Keep in dry area.

For full safety data refer to the products Material Safety Data Sheet. Observe precautions as per label.

### CONDITIONS OF USE AND DISCLAIMER

The information contained in this data sheet is given in good faith based upon our knowledge and current information and does not imply warranty. The information is provided and the product sold on the basis that the product is used for its intended use and applied in a proper workman like manner in accordance with the instruction in this data sheet onto suitable and correctly prepared surfaces which shall remain sound, stable, free of structural defects, cracking, spalling concrete cancer, negative pressure, movement or other conditions that may effect the performance of the product. Deviations from application instructions may diminish or negate the performance of the product. Under no circumstances will the Company be liable for any loss, consequential or otherwise, arising from the use of the product. Liability is limited to the replacement of proven faulty product.

Information valid May 2018

**DURAM INDUSTRIES (PTY) LTD** ACN 002 968 809 ABN 77 002 968 809  
**The Ultimate in Waterproofing & Protective Coating Technology**

NEW SOUTH WALES: 51 Prince William Drive, Seven Hills, NSW 2147  
QUEENSLAND: Unit 4, 29 Collinsvale Street, Rocklea QLD 4106  
NEW ZEALAND: Consolidated Alloys (NZ) Ltd  
55 Maurice Rd, Penrose, Auckland, New Zealand

Tel: (02) 9624 4077 Fax: (02) 9624 4079  
Tel: (07) 3255 6478 Fax: (07) 3255 6258  
Tel: 001164 9 622 9110 Fax: 001164 9 622 9119  
Web: [www.dlmwallace.co.nz](http://www.dlmwallace.co.nz)